中国认可
国际互认
检测
TESTING
CNAS L0823

202019001121

推荐实验室

广州市微生物研究所有限公司

GUANG ZHOU INSTITUTE OF MICROBIOLOGY CO.,LTD.

检 测 报 告

TEST REPORT

Report Number	WJ20204158
Name of Sample	Bio Based Industrial Coatings
Applicant	Allcera B. V

GUANG ZHOU INSTITUTE OF MICROBIOLOGY CO.,LTD.

TEST REPORT

Date Received: Sept.24, 2020
Date Analyzed: Oct.13, 2020

Name of Sample	Bio Based Industrial Coatings	Source of Sample	Delivery
Applicant	Allcera B. V	Client Number	——
Manufacturer	Allcera B. V	Brand	——
Type and Specification	750ml	Quantity of Sample	1 set
Date of Production	——	State of Sample	Liquid
Batch Number	——	Packing of Sample	——
Standard and Methods	GB/T 30706—2014 Measurment method and evaluating of the antibacterial characteristics of photocatalysis materials under visible light irridation		
Items of Analysis	Antibacterial Rate ((*Escherichia coli* AS1.90, *Staphylococcus aureus* AS1.89, *Candida albicans* ATCC 10231, *Klebsiella pneumoniae* ATCC 4352, *Pseudomonas aeruginosa* ATCC 15442)		
Remarks	Light wavelength: 500 nm; Colour temperature: 500K; Light intensity: 1400lx; Illumination time: 24 h. This test report is the English additional Edition of WJ20204158 issued on Oct.21th,2020.		

GUANG ZHOU INSTITUTE OF MICROBIOLOGY CO.,LTD.

TEST REPORT

Date Received: Sept.24, 2020
Date Analyzed: Oct.13, 2020

Test Results

Number of Sample	Test Condition	Test Bacteria				
		Escherichia coli	*Staphylococcus aureus*	*Candida albicans*	*Klebsiella pneumoniae*	*Pseudomonas aeruginosa*
WJ20204158-1	Bacteria Count of 0h Control Sample (cfu)	2.0×10^5	2.0×10^5	2.6×10^5	2.1×10^5	2.1×10^5
	Bacteria Count of Treatment after Control Sample in Bright Condition(cfu)	1.1×10^7	1.9×10^6	1.3×10^6	6.4×10^6	1.0×10^7
	Bacteria Count of Treatment after Control Sample in Dark Condition(cfu)	1.6×10^7	2.0×10^6	3.5×10^6	7.2×10^6	3.0×10^7
	Bacteria Count of Treatment after Test Sample in Bright Condition(cfu)	3.1×10^5	1.9×10^5	7.0×10^4	3.9×10^5	2.0×10^4
	Bacteria Count of Treatment after Test Sample in Dark Condition(cfu)	1.7×10^5	2.1×10^5	6.8×10^4	7.6×10^5	9.0×10^5
	Total Antibacterial Rate $R_{总}$(%)	97.2	90.0	94.6	93.9	99.8
	Photocatalytic antibacterial contribution Rate $R_{光}$ (%)	0.0	9.5	0.0	48.7	97.8

Note: According to the test method of this standard, the evaluation of total antibacterial rate ($R_{总}$) is: antibacterial rate≥90%, products have antibacterial effect; antibacterial rate≥99%, products have strong antibacterial effect.

End of report

Editor 钟伟松 Checker 袁志敏 Issuer 李四年 Date Reported 2020.10.23

Statements

1. The report would be invalid under the following conditions: altered, added, deleted, copied, without the specail seal for inspection or signtures by approver.
2. For the received sample , the sample information in the report is claimed by the applicant, the inspection unit is not responsible for its authenticity. The report is responsibility for the received sample only.
3. If there is any objection to the inspection report, it should be presented to the inspection unit within 15 working days from the issuance date, otherwise the report shall be deemed as having been accepted. Microbiological item is not subjected to retest.
4. The report and the name of the inspection unit shall not be used for product labels, advertisements, awards and merchandise publicity.。
5. The items marked with"*"in the report are not accredited by CNAS or CMA, The items marked with"#"are not accredited by CNAS, The items marked with"+"are not accredited by CMA.
6. The test data and results of items which are not accredited by CMA, only Used as scientific research, teaching or internal quality control.
7. Any ambiguity by the language which used in the report, the Chinese shall prevaile.

Contact Address,1Jiantashan Road，Huangpu District，Guangzhou City，Guangdong Province

Test Address,　(only fill in when it's different from the contact address)

Postal Code,510663

Tel.，(8620) 61302671

URL ,http://www.ggtest.com.cn